

# OLD TIME FINISH

Technical Sheet - Ed. 07/2020



**Lime putty finish with a marble effect, especially formulated for smooth, glossy skim coats. For indoor and outdoor use.**

## DESCRIPTION

Lime putty-based product containing marble powders and special additives, designed for smooth, glossy lime skim coats. Used on Old Time Max to obtain glossy, marble, encaustic finishes. For professional use.

## MAIN PROPERTIES

- Marble effect
- Breathable

## TECHNICAL DATA

Classification UNI 8681	Thick-coat paint for the topcoat in a one-pack, chemical-physical drying, matt finish, dispersed in water (C.4.C.O.D.2.C.SA)
Film aspect EN 13300	Matt ( $\leq 10$ gloss $85^\circ$ )
Maximum granulometry EN 13300	S1, Fine ( $< 100 \mu\text{m}$ )
Specific weight	$1440 \pm 50 \text{ g/l}$
pH	$> 11$
Type of binder	Lime
Solid content	$60 \pm 2\%$
Vapour permeability EN 1062	Sd $0.1 \pm 0.02 \text{ m}$ ; Class V1 High $\mu=100$
Water absorption EN 1062	Class W1, High
Drying time	Can be overpainted after 6 hrs, completely dry after 24 hrs
VOC	Cat A/l: limit 200 g/l (2010) This product contains a maximum of 80 g/l of VOCs

## CHARACTERISTICS

Colour range	Materia Naturale colour chart. Use of special colours that require organic pigments to achieve the tone are not recommended
Coverage	On two-coat plaster, in 2 coats: 1.1 mq/Kg (12 sq ft/Kg) On plaster skim coat, in 1 coat: 2.5 mq/Kg (27 sq ft/Kg)
Coverage per pack	(20 kg): 22 mq, approx. (2 coats) Coverage varies according to the roughness of the substrate.
Dilution	Ready to use; add a little water if necessary to achieve the right consistency
Diluted with	Water
Overpaintable	Compatibility with other products: water-based products

# OLD TIME FINISH

Technical Sheet - Ed. 07/2020

## APPLICATION

### Suitable Substrates:

Surfaces already prepared and treated with Old Times Max, mineral substrates

### Preparation of the Substrate:

Masonry substrates:

The substrates must be carefully prepared by manual brushing and/or by washing and/or pressure washer, depending on the nature and extent of the dirt on the surface to be treated. Any loose or friable paint must be removed. Apply a coat of Metro Fix.

Make sure that fresh plaster has set before applying.

Old Time Finish requires a perfectly smooth substrate.

### Application Procedure:

Mix until a smooth, lump-free mixture is obtained. Apply one or more coats with a stainless steel trowel. Always wait for the previous coat to dry before applying the next one. It must be polished using the same metal spatula while the previous coat is still slightly damp.

Marmorino effect application procedure

For marble finishes, the last coat is smoothed with a stainless steel trowel until the surface has a sleek, satin-finish. For an even greater shine or an encaustic effect, apply a coat of Old Time Finish over the Old Time Max and polish with a Pollock Stainless Steel trowel.

### Type of Equipment:

steel trowel (Pollock Stainless Steel trowel)

### Ambient Conditions:

Min +5°C max +40°C max RH 80%

## STORAGE

### Packaging:

20 Kg - 5 Kg - 1 Kg

### Duration and Preservation:

2 years when stored in undamaged packages at between 5 and 30°C; cannot endure frost and direct sunlight.

Dispose of in accordance with local regulations.

For information on possible hazards, refer to the safety data sheet.

## CERTIFICATION\CLASSIFICATION

