



## Alkali resistant acrylic fixative

### DESCRIPTION

Professional water-based fixative with good penetration and resistance to alkali, formulated to consolidate and uniform absorption on internal and external plasters. Particularly suitable for mineral substrates, suitable for the preparation of building surfaces intended to be covered with water-based paints or coatings. For indoors and outdoors.

### MAIN PROPERTIES

- Specific for cement-based smoothing compound
- Unsaponifiable
- Water repellent

### TECHNICAL DATA

Thickness EN 13300	Class A, fine (< 100 µm)
Classification (UNI 8681 / UNI 8682)	One-pack, physical drying, acrylic consolidating primer dispersed in water, for simple surface impregnation, matt finish (G.O.C.O.A.2.FA)
Specific weight	1020 ± 50 g/l
	7-8
Type of binder	Acrylic
Solid content	18 ± 2%
Drying time	Can be overpainted after 6 hrs, completely dry after 12 hrs
VOC	Cat A/h: limit 30 g/l (2010); this product contains a maximum of 1 g/l of VOCs

### CHARACTERISTICS

Coverage	With the application of 1 coat: 10-12 m <sup>2</sup> /l
Coverage per pack	(25 l): 300 m <sup>2</sup> , approx. Coverage varies according to substrate absorption.
Overpaintable	Compatibility with other products: compatible with all water-based products
Colour range	Transparent
Dilution	Water; 50% = 500 ml per litre of product

### APPLICATION

#### Suitable Substrates:

Cement-based plaster, lime-based plaster and paint, gypsum skimmed walls, mineral substrates, fibre cement, brick, wood, insulation panels

#### Ambient Conditions:

min +5°C max +35°C max RH 80%

#### Preparation of the Substrate:

All substrates must be free of release agents and must be dry, clean and coherent. Plasters must be sufficiently cured according to the type of material and manufacturer's instructions. On surfaces with mould or algae, first apply a coat of Sana Solux and wait at least 24 hours before proceeding as indicated in the technical data sheet. In the case of old, peeled and deteriorated paints, removal is recommended.

#### Type of Equipment:

brush, roller

#### Application Procedure:

Dilute PRIMACRIL as indicated and mix with a low speed mixer. Apply one coat and cross the direction of brush strokes

during application.

N.B.: always check that the treated surface is not glossy, if necessary increase the dilution.

## STORAGE

### **Disposal and safety indications:**

Dispose of in accordance with local regulations.

For information on possible hazards, refer to the safety data sheet

### **Packaging:**

25 l - 5 l - 1 l

### **Storage:**

1 year when stored in undamaged packages at between 5 and 30°C; cannot endure frost and direct sunlight