


# PRIMER RA


Technical Sheet - Ed. 06/2021



COMPANY  
WITH QUALITY  
MANAGEMENT  
SYSTEM  
CERTIFIED



INDOOR



OUTDOOR



WATER  
BASED



BRUSH



ROLLER

## Adhesion promoter on poorly absorbent substrates

### DESCRIPTION

Semi-transparent yellow adhesion promoter primer with a rough effect. It contains acrylic resins in emulsion and silica inert materials of such particle size as to produce a rough surface. Specially designed to facilitate adhesion of plaster or cement-based skim coats on smooth or poorly absorbent substrates. For professional use. For indoor and outdoor use.

### MAIN PROPERTIES

- Adhesion promoter
- semi-opaque
- Rough

### TECHNICAL DATA

Classification UNI 8681	One-pack, physical drying, acrylic base coat primer dispersed in water, containing other modifiers. Matt finish. (A.2.C.0.A.2.FD)
Film appearance EN 13300	Matt ( $\leq 10$ gloss $85^\circ$ )
Thickness EN 13300	Class B, medium ( $100 > 300 \mu\text{m}$ )
Specific weight	$1650 \pm 50 \text{ g/l}$
pH	n.p.
Type of binder	Styrene Acrylic
Solid content	$72 \pm 2\%$
Drying time	Touch dry after 2 hours. Under standard environmental conditions, it can be overpainted after 24 hours. In case of low temperatures or high humidity, drying times can vary considerably.
VOC	Cat A/c: limit $40 \text{ g/l}$ (2010) This product contains a maximum of $20 \text{ g/l}$ of VOCs

# PRIMER RA

Technical Sheet - Ed. 06/2021



COMPANY  
WITH QUALITY  
MANAGEMENT  
SYSTEM  
CERTIFIED



## CHARACTERISTICS

Colour range	Yellow
Coverage	With the application of 1 coat: 5-6 m <sup>2</sup> /l
Coverage per pack	Per package (14 l): 84 m <sup>2</sup> , approx. Coverage varies according to substrate absorption.
Dilution	50% = 500 ml per litre of product
Diluted with	Water
Overpaintable	With plaster and/or skim coats between 8 and 24 hours after application (but not more than 3 days)

## APPLICATION

### Suitable Substrates:

Reinforced concrete, precast concrete features, fibre cement, plasterboard, etc.

### Preparation of the Substrates:

All substrates must be free of release agents and must be dry, clean and coherent. Plasters must be sufficiently cured according to the type of material and manufacturer's instructions. On surfaces with mould or algae, first apply a coat of Sana Solux and wait at least 24 hours before proceeding as indicated in the technical data sheet. In the case of old, peeled and deteriorated paints, removal is recommended.

### Application Procedure:

Dilute PRIMEX RA as indicated and mix with a low speed mixer. Apply one coat and cross the direction of brush strokes during application.

During application, stir the product occasionally.

### Type of Equipment:

brush, roller

### Ambient Conditions:

min +5°C max +35°C max RH 80%

## STORAGE

### Packaging:

14 l – 4 l

### Duration and conservation:

1 year when stored in undamaged packages at between 5 and 30°C; cannot endure frost and direct sunlight

Dispose of in accordance with local regulations.

For information on possible hazards, refer to the safety data sheet

## TECHNOLOGIES/CERTIFICATIONS