



Decorative textured topcoat

DESCRIPTION

Decorative textured topcoat. Ideal for prime quality finishes, gives the surface an opaque, velvety metallic effect washable. For indoor use. For professional use.

MAIN PROPERTIES

- Metallic matt finish
- In relief



TECHNICAL DATA

Classification UNI 8681	Thick-coat paint for the topcoat: one-pack, physical drying, semi-gloss, acrylic, dispersed in water (B4.C.O.A.0.FA).
Film appearance EN 13300	Matt (≤ 10 gloss 85°)
Thickness EN 13300	Class A, fine ($< 100 \mu\text{m}$)
Specific weight	$1280 \pm 50 \text{ g/l}$
pH	7-8
Type of binder	Acrylic
Solid content	$55 \pm 2\%$
Drying time	Can be overpainted after 4 hrs, completely dry after 24 hrs
VOC	Cat A/i: limit 140 g/l (2010) This product contains a maximum of 42 g/l of VOCs

CHARACTERISTICS

Colour range	Senso colour chart. Can be coloured by tinting machine.
Coverage	Coverage with 1 coat: $4\text{-}5 \text{ m}^2/\text{l}$ ($43\text{-}54 \text{ sq ft/l}$) the coverage varies according to the desired effect
Coverage per pack	(5 l): $15\text{-}25 \text{ m}^2$, approx. Coverage varies according to substrate absorption.
Dilution	Ready to use
Diluted with	Water
Overpaintable	Compatibility with other products: all solvent free products

APPLICATION**Suitable Substrates:**

Cement-based plaster, painted plaster, gypsum skimmed walls, exposed reinforced concrete, precast concrete panels, fibre cement and wood.

Preparation of the Substrate:

Masonry substrates:

The substrates should be thoroughly prepared by brushing manually. Poorly adhering coats of old paint should be removed. Make sure that fresh plaster has set before applying. Application of one coat of Metro Fix.

Pre-painted or varnished wood substrates:

Partially or entirely scrape to remove any loose paint or varnish remaining or remove the paint entirely using chemical solvent paint stripper.

New or old wood substrates pre-treated as above:

Spot fill any gaps and micro-cracks using Metro Stuc.

Lightly sand to make the surface to be treated smooth and even.

Apply one coat of Metro Fix and sand lightly. Next, check the soundness of the substrate: if there is any dusting or if there are loose areas, another coat of Metro Fix should be applied.

Application Procedure:

Steel Effect

Apply two skim coats of Senso using a Pollock Stainless Steel trowel, working in different directions to achieve a wavy effect.

Industrial Effect

Apply an initial skim coat of Senso with a Pollock Stainless Steel trowel. When dry, apply a thick second coat and work the surface in a chessboard pattern using the broad side of the trowel and holding it flat. After a few minutes, when the product has started to dry, smooth the surface with the narrow part of the trowel, highlighting the horizontal and vertical scratches.

Textile effect

Apply a thick coat of Senso using vertical brush strokes. When the product has started to dry, smooth the surface with a Pollock Stainless Steel trowel to achieve a lined effect.

Notes:

For each specific area, we recommend using product from the same batch, otherwise there may be slight differences in shade.

Type of Equipment:

Brush (Klimt brush), stainless steel trowel (Pollock Stainless Steel trowel)

Ambient Conditions:

Min +5°C max +40°C max RH 80%

STORAGE**Packaging:**

5 l - 2.5 l - 1 l

Duration and Preservation:

2 years when stored in undamaged packages at between 5 and 30°C; cannot endure frost and direct sunlight.

Dispose of in accordance with local regulations.

For information on possible hazards, refer to the safety data sheet.

TECHNOLOGIES/CERTIFICATIONS

Ivas Industria Vernici S.p.A. – Via Bellaria, 40 – 47030 San Mauro Pascoli (FC) – Italy

Phone: +39 0541 815811 – Fax +39 0541 815815 - www.gruppoivas.com – ivas@gruppoivas.com

Company with quality management system certified UNI EN ISO 9001